

DMH 310 H-NBR Highly saturated nitrile butadiene rubber Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				green	green
hardness	23°C	ISO 868	Shore A	85 ± 5	Shore A 85 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 10	psi ≥ 1450
tensile strength	23°C	DIN 53 504	MPa	≥ 20	psi ≥ 2900
elongation at break	23°C	DIN 53 504	%	≥ 190	% ≥ 190
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 15	lbf/inch ≥ 85
spec. gravity	23°C	ISO 1183	kg/m ³	1320	g/cm ³ 1,32
rebound elasticity	23°C	DIN 53 512	%	29	% 29
abrasion	23°C	DIN 53 516	mm ³	135	mm ³ 135
compression set	*	ISO 815	%	≤ 12	% ≤ 12
compression set	**	ISO 815	%	≤ 14	% ≤ 14
compression set	***	ISO 815	%	≤ 22	% ≤ 22
minimum service temperature			°C	-20	°F -4
maximum service temperature			°C	150	°F 302
temp. max water/steam			°C	120	°F 248
temp. max hot air			°C	180	°F 356

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on butadiene and acrylonitrile

Resistant to: oil, petrol, hot water, hot air, ozone and crude oil

Not resistant to: conc. Acides, conc. lyes and polar solvents

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014