

DMH 335 EPDM KTW FDA Ethylene propylene diene rubber Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				black	black
hardness	23°C	ISO 868	Shore A	81 ± 5	81 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 5	≥ 725
tensile strength	23°C	DIN 53 504	MPa	≥ 12	≥ 1740
elongation at break	23°C	DIN 53 504	%	150	150
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 8	≥ 45
spec. gravity	23°C	ISO 1183	kg/m ³	1170	1,17
rebound elasticity	23°C	DIN 53 512	%	41	41
abrasion	23°C	DIN 53 516	mm ³		
compression set	*	ISO 815	%	≤ 15	≤ 15
compression set	**	ISO 815	%		
compression set	***	ISO 815	%		
minimum service temperature			°C	-40	-40
maximum service temperature			°C	130	266
temp. max water/steam			°C	130	266
temp. max hot air			°C	150	302

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on ethylene, propylene and diene

Resistant to: (hot) water, acids, bases, ketones, lyes, brake fluids based on polyglycols

Not resistant to: aliphatic, aromatic and chlorinated hydrocarbons, greases and fuels

Foodstuff approval: DVGW W-270 D1/D2, KTW D1 und D2

Maximum recommended service temperature (KTW applications): 60°C

BS 6920 cold water, FDA, 1935/2004

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500


E: office@dmh.at  www.dmh.at



DMH

SOLUTION FOR SEALS

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11
T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500
E: office@dmh.at  www.dmh.at

