

## DMH 300 NBR Nitrile butadiene rubber

### Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				<b>black</b>	<b>black</b>
hardness	23°C	ISO 868	Shore A	<b>85 ± 5</b>	Shore A <b>85 ± 5</b>
modulus 100%	23°C	DIN 53 504	MPa	<b>≥ 11</b>	psi <b>≥ 1595</b>
tensile strength	23°C	DIN 53 504	MPa	<b>≥ 17</b>	psi <b>≥ 2465</b>
elongation at break	23°C	DIN 53 504	%	<b>≥ 150</b>	% <b>≥ 150</b>
tear strength	23°C	DIN ISO 34-1	kN/m	<b>≥ 18</b>	lbf/inch <b>≥ 102</b>
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	<b>1280</b>	g/cm <sup>3</sup> <b>1,28</b>
rebound elasticity	23°C	DIN 53 512	%	<b>20</b>	% <b>20</b>
abrasion	23°C	DIN 53 516	mm <sup>3</sup>	<b>100</b>	mm <sup>3</sup> <b>100</b>
compression set	*	ISO 815	%	<b>≤ 5</b>	% <b>≤ 5</b>
compression set	**	ISO 815	%	<b>≤ 6</b>	% <b>≤ 6</b>
compression set	***	ISO 815	%		%
minimum service temperature			°C	<b>-30</b>	°F <b>-22</b>
maximum service temperature			°C	<b>110</b>	°F <b>230</b>
temp. max water/steam			°C		°F
temp. max hot air			°C		°F

\* 24h 70°C 25% def.

\*\* 24h 100°C 25% def.

\*\*\* 24h 150°C 25% def.

### Chemical Properties

Copolymer, based on butadiene and acrylonitrile

Resistant to: oil, petrol and crude oil

Not resistant to: conc. acids, conc. lyes and polar solvents

Foodstuff approval: -

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014

**DMH Dichtungs- und Maschinenhandel GmbH**

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500

E: office@dmh.at  www.dmh.at

