

DMH 301 NBR white Nitrile butadiene rubber

Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				white	white
hardness	23°C	ISO 868	Shore A	85 ± 5	85 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 8	≥ 1160
tensile strength	23°C	DIN 53 504	MPa	≥ 15	≥ 1450
elongation at break	23°C	DIN 53 504	%	≥ 200	≥ 200
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 18	≥ 102
spec. gravity	23°C	ISO 1183	kg/m ³	1440	1,44
rebound elasticity	23°C	DIN 53 512	%	23	23
abrasion	23°C	DIN 53 516	mm ³	140	140
compression set	*	ISO 815	%	≤ 7	≤ 7
compression set	**	ISO 815	%	≤ 9	≤ 9
compression set	***	ISO 815	%		
minimum service temperature			°C	-30	-22
maximum service temperature			°C	110	230
temp. max water/steam			°C		
temp. max hot air			°C		

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on butadiene and acrylonitrile

Resistant to: oil, petrol, hot air, ozone and crude oil

Not resistant to: conc. acids, conc. lyes and polar solvents

Foodstuff approval: -

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500

E: office@dmh.at  www.dmh.at

