

DMH 350 FPM/Viton Fluoro Rubber Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit	
colour				brown	brown	
hardness	23°C	ISO 868	Shore A	82 ± 5	82 ± 5	
modulus 100%	23°C	DIN 53 504	MPa	≥ 6	psi	≥ 870
tensile strength	23°C	DIN 53 504	MPa	≥ 9	psi	≥ 1305
elongation at break	23°C	DIN 53 504	%	≥ 200	%	≥ 200
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 20	lbf/inch	≥ 114
spec. gravity	23°C	ISO 1183	kg/m ³	2530	g/cm ³	2,53
rebound elasticity	23°C	DIN 53 512	%	7	%	7
abrasion	23°C	DIN 53 516	mm ³	175	mm ³	175
compression set	*	ISO 815	%	≤ 17	%	≤ 17
compression set	**	ISO 815	%	≤ 10	%	≤ 10
compression set	***	ISO 815	%	≤ 15	%	≤ 15
minimum service temperature			°C	-20	°F	-4
maximum service temperature			°C	220	°F	428
temp. max water/steam			°C		°F	
temp. max hot air			°C	300 short	°F	572 short

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 175°C 25% def.

Chemical Properties

Copolymer, based on fluoro

Resistant to: fats, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons

Not resistant to: glycols, ketones, most fluids containing amines, water/steam

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch ☉ Industriepark West 11

T: +43 (0)3833/200 60-0 ☉ F: +43 (0)3833/200 60-500

E: office@dmh.at ☉ www.dmh.at

