

DMH 352 FPM/Viton black Fluor Rubber Mechanical, Physical and Thermal Properties

properties	condition	standard	unit	unit	unit
colour				black	black
hardness	23°C	ISO 868	Shore A	85 ± 5	Shore A 85 ± 5
modulus 100%	23°C	DIN 53 504	MPa	≥ 7	psi ≥ 1015
tensile strength	23°C	DIN 53 504	MPa	≥ 9	psi ≥ 1305
elongation at break	23°C	DIN 53 504	%	≥ 140	% ≥ 140
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 7	lbf/inch ≥ 39
spec. gravity	23°C	ISO 1183	kg/m ³	1870	g/cm ³ 1,87
rebound elasticity	23°C	DIN 53 512	%	9	% 9
abrasion	23°C	DIN 53 516	mm ³		mm ³
compression set	*	ISO 815	%	≤ 13	% ≤ 13
compression set	**	ISO 815	%	≤	% ≤
compression set	***	ISO 815	%	≤	% ≤
minimum service temperature			°C	-20	°F -4
maximum service temperature			°C	210	°F 410
temp. max water/steam			°C		°F
temp. max hot air			°C	280 short	°F 536 short

* 24h 70°C 25% def.

** 24h 100°C 25% def.

*** 24h 175°C 25% def.

Chemical Properties

Copolymer, based on fluoro

Resistant to: fats, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons

Not resistant to: glycols, ketones, most fluids containing amines, water/steam

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH GmbH

revision: 03-2014

DMH Dichtungs- und Maschinenhandel GmbH

A-8772 Traboch  Industriepark West 11

T: +43 (0)3833/200 60-0  F: +43 (0)3833/200 60-500

E: office@dmh.at  www.dmh.at

